


Particle Size Distribution to BS 1377 : Part 2 :1990 Section 9.1 Wet Sieving Method

Scheme: NDR Aggregates

Location: Sand 0m

Location and orientation within sample not applicable

Bulk disturbed sample



Sieving	
Particle Size mm	% Passing
125	100
90	100
75	100
63	100
37.5	100
20	100
14	100
10	98
6.3	98
5	98
2	98
1.18	97
0.600	96
0.425	95
0.300	87
0.212	70
0.063	14

Specification for Highway Works Classification
Table 6/2

This material complies with the following material classes 1B, 6E/6R, 6J.

Moisture content % 8.8

Sample Proportions	
BOULDERS	0
COBBLES	0
Coarse GRAVEL	0
Medium GRAVEL	2
Fine GRAVEL	0
Coarse SAND	1
Medium SAND	27
Fine SAND	56
Silt & Clay	14

Grading Analysis	
D100	10
D60	0.19
D10	0.03
Uniformity Coefficient	6

Description	
Orangey brown fine to medium silty SAND	

* Uniformity coefficient extrapolated

Test Code = 610



Simon Holden (Project Technician)